

**GEORGIA DEPARTMENT OF TRANSPORTATION
STATE OF GEORGIA**

SUPPLEMENTAL SPECIFICATION

Section 413—Bituminous Tack Coat

413.1 General Description

This work includes furnishing and applying a bituminous tack coat on a prepared road surface including cleaning the road surface.

413.1.01 Definitions

General Provisions 101 through 150.

413.1.02 Related References

A. Standard Specifications

[Section 109—Measurement and Payment](#)

[Section 400—Hot Mix Asphaltic Concrete Construction](#)

[Section 424—Bituminous Surface Treatment](#)

[Section 427—Emulsified Asphalt Slurry Seal](#)

[Section 820—Asphalt Cement](#)

[Section 824—Cationic Asphalt Emulsion](#)

B. Referenced Documents

General Provisions 101 through 150.

413.1.03 Submittals

General Provisions 101 through 150.

413.2 Materials

Ensure that materials meet the following Specifications:

Material	Section
Asphalt cement, performance grade PG 58-22, PG 64-22, or PG 67-22	820.2.01
Cationic emulsified asphalt CRS-2h or CRS-3	824.2.01

Asphalt cement of performance grade PG 58-22, PG 64-22 or PG 67-22 is used for bituminous tack coat in work performed in [Section 400](#). Use cationic emulsified asphalt as a special application material only with prior written approval from the Office of Materials and Research.

The Department may change the grade or type of bituminous materials without a change in the Contract Unit Price if the Engineer determines that the grade or type selected is not performing satisfactorily.

= Change

413.2.01 Delivery, Storage, and Handling

General Provisions 101 through 150.

413.3 Construction Requirements

413.3.01 Personnel

General Provisions 101 through 150.

413.3.02 Equipment

Provide equipment in good repair, including the following units that meet the requirements of [Subsection 424.3.02, Equipment.](#)”

- Power broom and blower
- Pressure distributor

413.3.03 Preparation

General Provisions 101 through 150.

413.3.04 Fabrication

General Provisions 101 through 150.

413.3.05 Construction

A. Seasonal and Weather Limitation

Do not apply tack coat if the existing surface is wet or frozen. Do not place emulsified asphalt if the air temperature in the shade is less than 45 °F (7 °C).

B. Application

Coat the entire areas to be paved with the tack coat unless directed otherwise by the Engineer. Apply tack coat with distributor spray bars instead of hand hoses, except in small areas that are inaccessible to spray bars.

C. Temperature of Material

Apply bituminous materials within the temperature ranges specified below.

Bituminous Materials	Temperature of Application °F (°C)
Asphalt cement	350 - 400 (175 - 205)
CRS-2h	140 - 180 (60 - 80)
CRS-3	140 - 180 (60 - 80)

D. Cleaning

Immediately before applying the tack coat, clean the entire area free of loose dirt, clay, and other foreign materials.

E. Application Rate

The Engineer will determine the application rate of the bituminous tack coat.

F. Limitations and Areas Coated

Apply only enough tack coat to the prepared road surface that can be covered with the new pavement course the same working day the tack coat is applied.

G. Maintenance and Protection

After applying the tack coat material, allow it to cure until it is tacky enough to receive the surface course. Do not allow traffic on the tack.

= Change

413.3.06 Quality Acceptance

General Provisions 101 through 150.

413.3.07 Contractor Warranty and Maintenance

General Provisions 101 through 150.

413.4 Measurement

Bituminous materials for tack coat applied and accepted are measured as outlined in [Subsection 109.02, "Measurement of Bituminous Materials."](#)

Diluting emulsified tack coat is not ordinarily allowed except when used underneath slurry seal. The composition of diluted emulsified tack coat defined in [Subsection 427.3.05, "Construction"](#) is measured by the gallon (liter) of diluted mix.

413.4.01 Limits

General Provisions 101 through 150.

413.5 Payment

The accepted volume of bituminous material will be paid for at the Contract Unit Price per gallon (liter) for bituminous tack coat of the type and grade approved by the Engineer, complete in place. Payment is full compensation for preparing, cleaning, furnishing, hauling, applying material, and providing incidentals to complete the work.

Payment will be made under:

Item No. 413	Bituminous tack coat	Per gallon (liter)
Item No. 413	Diluted emulsified asphalt tack coat	Per gallon (liter)

= Change